



Zombie Dry Absorbent

STARFIRE ZOMBIE DRY ABSORBENT is kiln-dried, calcined and milled natural Montmorillonite Clay (CAS # 70892-59-0) with lower bulk density, higher sorptive capacity, higher surface area and high hardness (low solubility).

SCREEN SIZE: *

U.S.A. Standard Test Sieve (ASTME-II)

- +10 MESH5%
- +20 MESH50%
- +50 MESH40%
- + PAN<5 %

(100.00 %) *Typical analysis of standard product, individual results may vary.

TYPICAL CHARACTERIZATION	TYPICAL VALUES
LOOSE BULK DENSITY	37 - 39 LBS./CU. FT.
MOISTURE CONTENT	< 0.5%
HARDNESS	> 95%
PH	6.5
CEC	33.6
WATER ABSORPTION	78%
OIL ABSORPTION	76%
PRODUCT POROSITY	78%
GRANULATION	FINE



Multi-Purpose Absorbent

STARFIRE MULTI-PURPOSE ABSORBENT is kiln-dried, calcined and milled natural Montmorillonite Clay (CAS # 70892-59-0) with medium bulk density, medium sorptive capacity, average surface area and high hardness (low solubility).

SCREEN SIZE: *

U.S.A. Standard Test Sieve (ASTME II)

- + 4 MESH0%
- + 6 MESH16%
- + 10 MESH40%
- + 20 MESH35%
- + 30 MESH5%
- + 60 MESH<5%
- + PAN<0.5%

(100.00%) *Typical analysis of standard product, individual results may vary.

TYPICAL CHARACTERIZATION	TYPICAL VALUES
LOOSE BULK DENSITY	40 - 42 LBS./CU. FT.
MOISTURE CONTENT	< 0.5%
HARDNESS	> 95%
PH	6.0 - 6.5
CEC	33.6
WATER ABSORPTION	72%
OIL ABSORPTION	53%
PRODUCT POROSITY	78%
GRANULATION	COARSE

